

TEST REPORT

NUMBER : DELH25002688
DATE : 28TH FEB, 2025



TEST REPORT

NUMBER : DELH25002688
DATE : 28TH FEB, 2025

APPLICANT: SHREE PRAGYA TECHPACK PRIVATE LIMITED

ATTN: PRAKHAR JAIN

SAMPLE DESCRIPTION: PE CLING FILM

DATE RECEIVED : 17TH FEB, 2025
TEST PERFORMANCE DATE : 17TH FEB, 2025 TO 28TH FEB, 2025
BUYER'S NAME : --
BUYING AGENT/ CONTACT : --
FIBER CONTENT : --
ORDER NO. : --
STYLE NO. : --
COLOR : --
END USE : --
SEASON : --
COUNTRY OF ORIGIN : INDIA
COUNTRY OF DESTINATION : --
MANUFACTURER'S NAME : --

TESTS CONDUCTED: AS PER THE REQUEST BY THE APPLICANT.
FOR FURTHER DETAILS PLEASE REFER TO THE ENCLOSED PAGE (S).

CONCLUSION:

TESTED SAMPLE	TEST PARAMETERS/STANDARD	RESULT
SUBMITTED SAMPLE	OVERALL MIGRATION (Food Safety and Standards (Packaging) Regulations, 2018/IS:9845:2020)	M

NOTE: M = MEET CLIENT'S REQUIREMENT F = NOT MEET CLIENT'S REQUIREMENT
= NO SPECIFIED REQUIREMENT N/A = NOT APPLICABLE

Note:

1. Statement of conformity is based on the simple acceptance rule without using measurement uncertainty.
2. In this report results relate only to the item tested.
3. Laboratory reports the final test results in test report. Any additional information, if required will be provided on request.
4. Samples received in good condition.
5. Testing has been performed as per the applicant's request.
6. Sampling is not done by Laboratory.

AUTHORIZED BY
FOR INTERTEK INDIA PVT. LTD



SUDHANSHU KUMAR
LAB MANAGER – HARDLINES AND TOYS



TEST REPORT

NUMBER : DELH25002688
DATE : 28TH FEB, 2025

TEST CONDUCTED:

1.OVERALL MIGRATION TEST:

Test Specification: Food Safety and Standards (Packaging) Regulations, 2018

Test Method: IS 9845:1998 Reaffirmed 2020

Simulant volume: 200 ml

Simulant Used	Test Condition	Test Result (mg/dm ²)	Requirement (mg/dm ²)
Distilled water	40°C for 10 days	< 5.0	< 10
3% Acetic acid	40°C for 10 days	< 5.0	< 10
10% Ethanol	40°C for 10 days	< 5.0	< 10
n-Heptane	38°C for 30 Min	< 5.0	< 10
50% Ethanol	40°C for 10 days	< 5.0	< 10

Tested Item: PE CLING FILM

END OF TEST REPORT

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or willful misconduct.

